

SARL POROTECHNIC

Zone de légrin

Route de St Gilles

30132 CAISSARGUES

Tel. 04.66.38.38.20

www.porotechnic.com

CLEAR INTERNAL NATURAL TREATMENT:

The cleaning being ended, after 8 days of drying **ANTISALP proton coal equivalent CLEAR " S " (ancient STOPFAT SLV) NATURAL WAX:**

- Pulverize 2 coats of ANTISALP definitely wipe surplus (puddles) with one rag. 1st very generous coat in the morning, 2nd in the afternoon
- 24 hours after POROSTOP,
- Apply PROTON COAL EQUIVALENT CLEAR " S " in 2 coats at 24 hours of space. Wait 10 minutes and wipe surplus with a rag (after every coat).
- The following day, to cross 2 - 3 coats of natural wax. Polish up between coats in the help of a wool rag or a shoe-shine girl.
 - Natural wax is: PROCIR MILK (satiny aspect) PROCIR WAX (ancient POROWAX) in paste (shining more supported).

Translation by a generator.